

WOVEN FABRIC

Product Description: **TKB-170**
Aramid or PBO Fabric

| CHARACTERISTICS | NOMINAL | UM | TOLERANCE | NORMATIVE |
|--------------------|----------------|------------------|-----------|---------------|
| Mass unit per area | 173 | g/m ² | 5,0% | ISO 3374 |
| Weave | Plain | | | ISO 2113 |
| Width | from 10 to 200 | mm | 2,5% | ISO 22198 |
| Thickness | 0,17 | mm | 5,0% | ISO 5084 (**) |
| Other informations | Loomstate | | | |

| NOMINAL CONSTRUCTION | WARP | | WEFT | |
|---------------------------------|-------------------------------------|----------|-------------------------------------|--------------------|
| 1st fiber description | Aramid Fiber - Type 2200 - 1210dtex | | Aramid Fiber - Type 2200 - 1210dtex | |
| 1st fiber producer | Twaron | | Twaron | |
| 2nd fiber description | | | | |
| 2nd fiber producer | | | | |
| Thread count - 1st fiber | 6,50 ends/cm ±2% | ISO 4602 | 6,80 ends/cm ±2% | ISO 4602 |
| Thread count - 2nd fiber | | | | |
| Weight distribution - 1st fiber | 85 g/m ² | 49,1% | 88 g/m ² | 50,9% |
| Weight distribution - 2st fiber | | | | |
| Weight distribution | 49,1% | | 50,9% | |
| Selvages | Weaving style | LENO | Type of fiber | HM polyster 22 tex |

| MECHANICAL PROPERTIES OF FIBER | STRENGHT (nominal) | MODULUS (nominal) |
|--------------------------------|--------------------|-------------------|
| Type 2200 - 1210dtex | 3176 MPa | 108 GPa |
| | | |
| | | |

(**) Theoretical thickness for an epoxy laminate with 40% of reinforcement in volume.

Note: Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.

ANGELONI GROUP

Via Abbate Tommaso 72/A 30020 Quarto D'Altino (VE) - Italy
T. +39 0422 780580 - F. +39 0422 782787
E. info@angelonigroup.com

angelonigroup.com