

Main features

- based on modified waxes and silicones
- dissolved in volatile benzines
- quick drying
- mild smelling
- compliant with FDA 21CFR177.2600

Applications

- universal release agent
- specially for the release of epoxy resins and polyurethanes on metallic and sucking* substrates

Properties in state upon delivery at 20 °C (approx. values)

Colour		milky/white
Density	g/cm ³	0.75
Application temperature up to	°C	100
Thermal stability	°C	170

How to process the material

Shake well prior to use. Apply the release agent thinly and evenly using a brush or spraying system. NEUKADUR release agent SE new is generally be overpainted and adhesively bonded (own pre-production tests are necessary). The dried surface can be polished easily.

Attention!! The contained solvents are highly inflammable. Do not smoke while processing the material.
No open flame. Hazard class A1 according to the regulation for combustible liquids.

* Recommended for the application on surfaces made from plaster is NEUKADUR release agent P6 FL.

Further release agents, please visit our homepage <http://www.altropol.de/en/produkte/weitere-produkte/trennmittel>

Form of delivery

NEUKADUR release agent SE new 1.5 kg 3.5 kg 20 kg

Storage

We recommend keeping the material in tightly closed original receptacles at temperatures of 20 - 25 °C. When duly stored, the material can be used within the shelf life indicated on the labels (the first 2 digits of the batch number indicate the week, the 3rd digit indicates the year).

Measure of precaution

With the aid of the current safety data sheets, which contain physical, ecological, toxicological and other data relating to safety, the user can inform himself on the safe handling and storage of the products.

Our technical service - in words, in writing or by trials - is given according to the current state of our knowledge. It does however not relieve the customer / user from the duty to check by himself if the products supplied by us are suitable for the intended processes and purposes. Application, use and processing of the products take place beyond our control possibilities and lie therefore exclusively in the area of responsibility of the processor. Any existing property rights of third parties are to be considered. We guarantee the perfect quality of our products in accordance with our general terms and conditions of business. When handling our products you have to observe the legal rules and the rules for the industrial hygiene. As for the rest, we refer to the corresponding safety data sheets

• 2021-03-12.5 / 12 / LW-W •